

1000 SERIES

TECHNICAL DATA



Issue no. 6 Issued February 2020

RA 1022 ALUMINIUM FOIL/FILM/SQUARE SCRIM LAMINATE TAPE

<u>TECHNICAL DETAILS</u>	<u>TYPICAL VALUE</u>	<u>UNITS</u>
Thickness, adhesive plus carrier	0.17	mm
Foil/film laminate	0.13	mm
* The foil scrim laminate has been approved to B.S476 fire standards		
Adhesive type	Rubber/resin	0
Release liner weight	62	g/sq.m.
Peel adhesion	1000	N/m
Polyester Loop Tack	900	N/m
Tensile strength, machine direction	4000	N/m
Tensile strength, cross direction	2100	N/m
Elongation at break	5	%
Service temperature range	-10 to 60	Deg. C.
Recommended application temperature range	5 to 25	Deg. C.
Moisture vapour permeability	Less than 1	g per sq. m., 24h at 40 deg C., 90% R.H.
Shear adhesion, 1Kg @23 deg. C.	15	Hours
Shelf life	12	Months

Test Methods: BS 3924:1978

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE
PRODUCTS Ltd

Darlaston Road Industrial Estate, Wednesbury
West Midlands, WS10 7TN U.K.
Tel: +44 (0)121-526 5151 Fax: +44 (0)121-568 6797
Email: sales@paladhesives.co.uk