

1000 SERIES

TECHNICAL DATA



Issue No. 6

Issued Feb 2016

RA 1100 SOLVENT ACRYLIC TRANSFER TAPE (Amber Release liner)

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Thickness of adhesive	0.03	mm
Release liner; Amber - double sided glassine	80	g per sq.m.
Adhesive coat weight	30 - 35	g per sq. m.
Peel adhesion*	600	N/m
Polyester loop tack	1250	N/m
Liner release	10 max.	N/m
Shear adhesion failure temperature (SAFT)	85 - 90	Deg. C.
Recommended application temperature	+5 to +25	Deg.C.
Service temperature range	-20 to +120	Deg. C.
UV resistance	Excellent	
Fungi resistance	Excellent	
Oxidation resistance	Excellent	
Weather resistance	Excellent	

Test Methods: BS 7116

* Value quoted after 10 mins dwell time

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE
PRODUCTS Ltd

Darlaston Rd Industrial Estate, Darlaston Rd, Wednesbury
West Midlands, WS10 7TN U.K.
Tel: +44 (0)121-526 5151 Fax: +44 (0)121- 568-6797
Email: sales@paladhesives.co.uk