

2000 SERIES

TECHNICAL DATA



Product datasheet Issue No 7 Issued Jan 16

RA 2012 DOUBLE-SIDED HIGH TACK TISSUE TAPE

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Adhesive Type	Pressure Sensitive Hot-Melt Rubber Resin	
Thickness, adhesive + carrier	0.085	mm
Release liner thickness	0.055	mm
180 degree peel adhesion:		
Open side	1100	N/m
Closed side	1100	N/m
Polyester loop tack:		
Open side	1000	N/m
Closed side	1000	N/m
Liner release	65	gsm
Tensile strength	1000	N/m
Elongation at break	4	%
Service temperature	-40 to +60	Deg. C.
Recommended application temperature	+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	> 50	Hours
Shelf life	12	Months

Test Methods: BS 7116

Standard fingerlift formats

6/12, 9/15, 12/18, 18/24, 24/30
Other formats, inc. offset fingerlift
available subject to min. quantities

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE
PRODUCTS Ltd

Darlaston Rd industrial Estate, Darlaston Rd, Wednesbury, WS10 7TN UK.
Email: sales@paladhesives.co.uk
Tel: +44 (0)121 - 526-5151

Fax: +44(0)121- 568-6797