

2000 SERIES

TECHNICAL DATA



Product datasheet Issue No. 5 Issued December 21

RA 2042 GLASS FIBRE SCRIM TAPE Polypropylene film release liner

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Adhesive Type : Pressure Sensitive Hot Melt / Rubber Resin

Thickness, adhesive + carrier	0.170	mm
Release liner thickness	45 μ White film	
180 degree peel adhesion:		
Open side	1200	N/m
Closed side	1200	N/m
Polyester loop tack:		
Open side	1000	N/m
Closed side	1000	N/m
Service temperature	-10 to +60	Deg. C.
Recommended application temperature	+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	50	Hours
Shelf life	12	Months

Test Methods: BS 7116

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE
PRODUCTS Ltd

Darlaston Road Ind. Estate, Darlaston Road, Wednesbury, WS10 7TN UK

Email: sales@paladhesives.co.uk

Tel: +44 (0)121 - 526 5151

Fax: +44(0)121- 568 6797