



Product datasheet Issue No. 8

Issued May 16

RA 2065 DOUBLE-SIDED GENERAL PURPOSE FINGERLIFT TISSUE TAPE

TECHNICAL DETAILS		TYPICAL VALUE	UNITS
Adhesive Type : Pressure Sensitive Hot Melt / Rubber Resin			
Thickness, adhesive + carrie Release liner thickness	r	0.085 0.055	mm mm
180 degree peel adhesion:	Open side Liner side	1000 1000	N/m N/m
Polyester loop tack:	Open side Liner side	1100 1100	N/m N/m
Liner release		65	gsm
Tensile strength		1100	N/m
Elongation at break		4	%
Service temperature		-10 to +60	Deg. C.
Recommended application temperature		+5 to +25	Deg. C.
Static shear adhesion, 1Kg @ 23 deg. C.		Greater than 100	Hours
Shelf life		12	Months
Standard product formats		6/12, 9/15, 12/18, 18/24, 24/30 Other formats, inc. offset fingerlift available subject to min quantities 175.105	mm
FDA Approval Test Methods: BS 7116			
THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY. ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR DETEMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.			



Darlaston Rd industrial Estate, Darlaston Rd, Wednesbury, WS10 7TN UK.

Email: sales@paladhesives.co.uk

Tel: +44 (0)121 - 526 5151 Fax: +44(0)121- 568 6797