

2000 SERIES

TECHNICAL DATA



Issue number 1

Issued Oct. 2004

RA 2336 REINFORCED PEELEABLE ACRYLIC TRANSFER TAPE

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Thickness adhesive plus carrier		0.060	mm
Release liner type		White glassine	
Release liner thickness		0.065	mm
Peel adhesion to steel:	Open side	120	N/m
	Liner side	120	N/m
Polyester loop tack	Open side	240	N/m
	Liner side	240	N/m
Liner release		65	gsm
Service temperature range		-10 to +100	Deg. C.
Recommended application temperature		+5 to +25	Deg. C
Shelf life		12	Months
Test Methods: B S 7116			

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



**PAL ADHESIVE
PRODUCTS Ltd**

Darlaston Road Ind. Estate, Darlaston Road, Wednesbury, WS10 7TN UK.
Email: sales@paladhesives.co.uk
Tel: +44 (0)121 - 526 5151

Fax: +44(0)121- 568 6797