

2000 SERIES

TECHNICAL DATA



Product datasheet Issue No. 3 Issued Dec 2021

RA 2732 ZCA DOUBLE SIDED GENERAL PURPOSE TISSUE TAPE

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Adhesive Type : Pressure Sensitive Hot Melt / Rubber Resin

Thickness, adhesive + carrier	0.105	mm
Release liner thickness	0.105	
180 degree peel adhesion:		
Open side	1100	N/m
Closed side	1100	N/m
Polyester loop tack:		
Open side	1200	N/m
Closed side	1200	N/m
Liner weight	110	gsm
Tensile strength	1100	N/m
Elongation at break	4	%
Service temperature	-40 to +60	Deg. C.
Recommended application temperature	+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	24	Hours
Shelf life	12	Months
Test Methods: BS 7116		BS 7116

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE
PRODUCTS Ltd

Darlaston Rd industrial Estate, Darlaston Rd Wednesbury, WS10 7SG UK
Email: sales@paladhesives.co.uk
Tel: +44 (0)121 - 526 5151

Fax: +44(0)121- 568 6797