

# 2000 SERIES

## TECHNICAL DATA



Product datasheet Issue No 3 Issued Sept 2022

### RA 2991F DOUBLE-SIDED POLYESTER FILM - BOX SEAL TAPE White Glassine Release Liner

#### TECHNICAL DETAILS

#### TYPICAL VALUE

#### UNITS

Adhesive Type : Pressure Sensitive Hot Melt / Rubber Resin

Thickness, adhesive + carrier	0.210	mm
Release liner thickness	90	gsm
180 degree peel adhesion:		
Open side	1000	N/m
Closed side	1400	N/m
24 Hour Dwell		
Open side	1600	N/m
Closed Side	2400	N/m
Polyester loop tack:		
Open side	1100	N/m
Closed side	1400	N/m
Liner release	10	N/m
Tensile strength	4600	N/m
Elongation at break	120	%
Service temperature	-10 TO +60	Deg. C.
Recommended application temperature	+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	>24	Hours
Shelf life	12	Months

Test Methods: BS 7116

The individual ingredients of the the adhesive have been tested and approved for indirect food contact to the FDA specification 175.105

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.  
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR  
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE  
PRODUCTS Ltd

Darlaston Rd industrial Estate, Darlaston Rd, Wednesbury, WS10 7TN  
UK. Email: sales@paladhesives.co.uk  
Tel: +44 (0)121 - 526 5151 Fax: +44(0)121- 505 6797