



Product datasheet Issue No 2

Issued Sept 2015

## RA 3225 PERM/PEEL FILMIC FINGERLIFT ACRYLIC DOUBLE-SIDED TAPE, AMBER PAPER LINER

TECHNICAL DETAILS	TYPICAL VALUE	<u>UNITS</u>
Thickness, adhesive + carrier Release liner thickness	0.050 0.075	mm mm
180 degree peel adhesion:  Closed side Polyester loop tack:  Open side Open side Closed side	400 150 800 100	N/m N/m N/m N/m
Liner release	10	N/m
Tensile strength Elongation at break	4600 12	N/m %
Service temperature	-20 TO +120	Deg. C.
Recommended application temperature	+5 TO +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	>2	Hours
Shelf life	12	Months
Standard product formats	6/12, 9/15, 12/18, 18/24, 24/30 Other formats, inc. offset fingerlift available subject to min. quantities	mm

Test Methods: BS 7116

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETEMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



Darlaston Rd industrial Estate, Darlaston Rd, Wednesbury, WS10 7TN UK.

Email: sales@paladhesives.co.uk

Tel: +44 (0)121 - 526 5151 Fax: +44(0)121- 505 6267