

PRODUCTS TECHNICAL DATA

Issue No. 1

Issued May 18

RA 8069A - DOUBLE-SIDED TISSUE TAPE SOLVENT ACRYLIC ADHESIVE - AMBER LINER

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Adhesive thickness	0.095	mm
Tolerance on thickness (+ or - 10 %)	min0.085 max 0.105	mm
Release liner type	Amber glassine	
Release liner thickness	0.08	mm
180 degree peel adhesion: Open side	700	N/m
Liner side	700	N/m
Polyester loop tack: Open side	1000	N/m
Liner side	1000	N/m
Liner release	10	N/m
Tensile strength	1000	N/m
Elongation at break	4	%
Shear adhesion, 1Kg @ 23 deg. C	>80	Hours
Temperature exposure short term	200 <1min	Deg. C.
Service temperature	-40 to +140	Deg. C.
Recommended application temperature	+5 to +25	Deg. C.
Shelf life	12	Months

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR DETERMINING THE
SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE
PRODUCTS Ltd

Darlaston Rd industrial Estate, Darlaston Rd Wednesbury, WS10 7T

Email: sales@paladhesives.co.uk

Tel: +44 (0)121 - 526 5151

Fax: +44(0)121- 568-6797

